

Building Specification Sheet for Armourcoat Duturo Finish Interior BSS14

Product:	Armourcoat Duturo Armourcoat Ltd. Morewood Close, London Road, Sevenoaks, Kent. TN13 2HU web: www.armourcoat.com
Location:	(eg. Walls and ceilings to reception area and lift lobby).
Drawings:	Refer to drawings no. ...
Background:	Substrate to be prepared in accordance with Armourcoat Ltd's guidance: <ul style="list-style-type: none">• Duturo Backgrounds and Applications (SSS8)
Preparation:	Coating is around 0.5mm thick and will follow contour of substrate. Surfaces should be sound and true with no hollows or bumps. Finish is not suited to margins less than 100mm wide. Substrates must be free of curing compounds, dust and other impurities such as oil, grease and salts and must be sealed with manufacturer's recommended primer. Remove all fixtures and fittings. Recommended background tolerance ± 1 mm in 600mm and ± 3 mm in 1800mm. Internal curves must be greater than 2m diameter. External curves must be greater than 300mm diameter. Surfaces curved in 3 planes such as domes cannot be coated.
Primer:	Apply 1 coat Armourcoat K40 Primer or diluted R13 Resin (substrate depending) and allow to dry .
Finish:	Apply 1 or 2 coats of pre-mixed Duturo (DT) and blade down progressively to a finish as it dries. (Optional) Apply Colourwash when Duturo is dry. (Optional) Apply Armourcoat sealer when Duturo or Colourwash are dry. (Necessary only in heavy traffic, vulnerable locations)
Thickness:	0.5 – 1.0 mm
Colour:	Duturo ref ... Colourwash ref ... Sealer ... yes / no
Guarantee:	10 year guarantee covering materials and application for internal use.
Application:	The system is to be supplied and applied by Armourcoat Surface Finishes.

Whilst every attempt has been made to ensure the accuracy and reliability of the information contained in this document, the information should not be relied upon as a substitute for formal advice. Armourcoat Ltd, its employees and agents will not be liable for any loss or damage, of any kind, arising out of or in connection with the use of this document. Please refer to the company disclaimer for further details.
SAT BSS14 0206©

Armourcoat Limited
Morewood Close London Road
Sevenoaks Kent TN13 2HU United Kingdom
Tel: +44 (0)1732 460 668 Fax +44 (0)1732 450 930
Email: technical@armourcoat.co.uk

web: www.armourcoat.com