



Building Specification Sheet For Squash Courts BSS15

GENERAL PLASTERING: ARMOURCOAT SQUASH COURT PLASTER

Product:	Armourcoat Squash Court Plaster
Manufacturer:	Armourcoat Ltd, Morewood Close, London Road, Sevenoaks, Kent. TN13 2HU, Tel +44 (0)1732 460668.
Location:	(eg. Walls to reception area and lift lobby)
Drawings:	Refer to drawings no
Background:	Apply directly to dense concrete blockwork (see Armourcoat Specifications)
Preparation:	Allow for a P.V.A.C.bonding agent as clause 565. Check with block manufacturer for recommendations.
Undercoat:	Armourcoat Squash Court Basecoat
Thickness:	Apply to a thickness of 9mm. Ensure at least 6mm over high spots.
Final coat:	Armourcoat Squash Court Topcoat.
Thickness:	Apply to a thickness of 3mm.
Finish:	Trowel to a smooth flat surface.
Accessories:	Angle beads, stop beads, all galvanised.

Whilst every attempt has been made to ensure the accuracy and reliability of the information contained in this document, the information should not be relied upon as a substitute for formal advice. Armourcoat Ltd, its employees and agents will not be liable for any loss or damage, of any kind, arising out of or in connection with the use of this document. Please refer to the company disclaimer for further details.

DMM BSS15 1201©