

Building Specification Sheet For High Impact Areas BSS21

ARMOURCOAT SQUASH COURT PLASTER ON ANTI-CRACK BASE WITH CLEARSEAL

Product:	Armourcoat AntiCrack base coat + Armourcoat Squash Court Plaster
Manufacturer:	Armourcoat Ltd, Morewood Close, London Road, Sevenoaks, Kent. TN13 2HU, Tel +44 (0)1732 460668.
Location:	(eg. Walls to New Magistrates Court)
Drawings:	Refer to drawings no
Background:	Apply directly to dense pre-cast concrete or blockwork (see Armourcoat Specifications)
Preparation:	Allow for a P.V.A.C. bonding agent as clause 565. Check with block manufacturer for recommendations.
Undercoat:	Armourcoat Anti-crack
Thickness:	Apply to a thickness of 6-8mm. Ensure at least 6mm over high spots.
Final coat:	Armourcoat Squash Court Topcoat.
Thickness:	Apply to a thickness of 2-3mm.
Finish:	Trowel to a smooth flat surface. Leave to dry.
Sealant:	Roller Armourcoat Clearseal to surface or Anti-Graffiti sealant where necessary.
Accessories:	Angle beads, stop beads, all galvanised.

Whilst every attempt has been made to ensure the accuracy and reliability of the information contained in this document, the information should not be relied upon as a substitute for formal advice. Armourcoat Ltd, its employees and agents will not be liable for any loss or damage, of any kind, arising out of or in connection with the use of this document. Please refer to the company disclaimer for further details.

SD BSS21 0304©