

Building Specification For Armourcoat Cloudy Finish BSS2

Product:	ARMOURCOAT Polished Plaster
Manufacturer:	Armourcoat Ltd. Morewood Close, London Road, Sevenoaks, Kent. TN13 2HU web: www.armourcoat.com
Location:	(e.g. Walls and ceilings to reception area and lift lobby)
Drawings:	Refer to drawings no.
Background:	Substrate to be prepared in accordance with Armourcoat Ltd's guidance: <ul style="list-style-type: none">• Plasterboard/Drylining Installation and Finishing (SSS1)• Plasterboard/Drylining with Armourcoat AntiCrack Skimcoat (SSS2)• Brick, Block and Concrete (SSS3)• Glasroc and GRG (SSS4)• Previously Decorated (SSS5)• Sand / Cement Render (SSS6)• MDF (SSS7)• Bluclad Board (SSS9)• Exterior Application (SSS10)
Preparation:	Ensure a true, flat and even surface with wall surfaces that are constructed in accordance with specialist's requirements. Substrates must be free of curing compounds, dust, and other impurities such as oil, grease and salts.
Primer:	For surfaces with uneven suction apply Armourcoat K40 Primer in accordance with manufacturers recommendations.
Keycoat:	Mix and apply Armourcoat Keycoat (K124 or K149) in accordance with manufacturer's working instructions.
Finish:	Apply 2 or 3 thin coats of Armourcoat pre-mixed plaster (CL) in successively thinner layers in one day. Exact number of coats to specialist's requirements and determined by the level of sheen required. Leave overnight before waxing.
Thickness:	approx. 1.5 mm – 2.0 mm
Colour:	Armourcoat ref: e.g. Cloudy X0081
Waxing:	Leave to dry overnight before waxing. Supply and apply Armourcoat wax polish (Ref. White Wax) sparingly in accordance with manufacturer's working instructions. Refer to Clause 250 in General Requirements.
Guarantee:	10 year guarantee covering materials and application for internal use.
Application:	The system is to be supplied and applied by Armourcoat Surface Finishes.

Whilst every attempt has been made to ensure the accuracy and reliability of the information contained in this document, the information should not be relied upon as a substitute for formal advice. Armourcoat Ltd, its employees and agents will not be liable for any loss or damage, of any kind, arising out of or in connection with the use of this document. Please refer to the company disclaimer for further details.
SPD BSS2 0206 ©