



Building Specification Sheet For External Application Armourcoat Of Sealed Armourcoat Polished Plaster BSS9

Product:	ARMOURCOAT Polished Plaster
Manufacturer:	Armourcoat Ltd. Morewood Close, London Road, Sevenoaks, Kent. TN13 2HU web: www.armourcoat.com
Location:	(e.g. Walls and ceilings to entrance areas)
Drawings:	Refer to drawings no.
Background:	Substrate to be prepared in accordance with Armourcoat Ltd's guidance: <ul style="list-style-type: none">• Bluclad Board (SSS9)
Preparation:	Ensure a true, flat and even surface with wall surfaces that are constructed in accordance with Bluclad board manufacturer's requirements. Substrates must be free of curing compounds, dust, and other impurities such as oil, grease and salts. Bluclad board to be finished with Dryvit Genesis Mesh System by ASF.
Keycoat:	Mix and apply Armourcoat Keycoat (K124 or K149) in accordance with manufacturer's working instructions.
Finish:	Apply Armourcoat Polished Plaster in accordance with manufacturer's working instructions. Leave for seven days.
Sealant:	2-3 coats of roller applied Trimite RJ150 to be applied seven days after final application of polished plaster.
Thickness:	approx. 4.0 mm – 5.0 mm including Dryvit Genesis Mesh System.
Colour:	Armourcoat ref: e.g. PT L6201 with Trimite RJ150.
Sealant:	Two coats of roller applied Trimite RJ150 to be applied seven days after final application of Pitted polished plaster.
Application:	The system is to be supplied and applied by Armourcoat Surface Finishes. Details of Bluclad installation to be advised by Eternit.

Whilst every attempt has been made to ensure the accuracy and reliability of the information contained in this document, the information should not be relied upon as a substitute for formal advice. Armourcoat Ltd, its employees and agents will not be liable for any loss or damage, of any kind, arising out of or in connection with the use of this document. Please refer to the company disclaimer for further details.

SPD BSS9 0206 ©

Armourcoat Limited
Morewood Close London Road
Sevenoaks Kent TN13 2HU United Kingdom
Tel: +44 (0)1732 460 668 Fax +44 (0)1732 450 930
Email: technical@armourcoat.co.uk

web: www.armourcoat.com