

## Product Data Sheet 21

### Squash Court Coating

#### 1 Product Description

Armourcoat Squash Court Coating is a two-part water dispersed epoxy coating. The product can be thinned with water, contains no solvents and therefore is non – flammable and odour free.

#### 2 Technical Data

Touch dry	-	6 – 8 hours
Shelf life	-	12 months
Pot life	-	60 minutes
Pack size	-	5.40kg (5.0litres)
Full cure	-	7 days
Open Court for Play	-	48 hours

#### 3 Surface Preparation

New plaster should be at least 14 days old. The substrate should be sound, clean and free from dust, oil, grease or any other agents that may affect adhesion. Cleaning techniques should be by mechanical means such as scrubbing with dilute cleaning solution and possibly sanding with medium grit sand paper. Prior to any overcoating all surface defects should be repaired with Armourcoat Squash Court Repair Pack.

Epoxy Coatings are prone to UV yellowing when regularly exposed to sunlight. Please be aware that the product may not be suitable on courts with natural light exposure. Please consult the technical department if further information is required.

#### 4 Mixing

Squash Court Coating is supplied in pre-weighed containers and is ready for mixing on site. The individual components of the product should be stirred before the two are mixed together. The entire contents of Resin Component A should be added to Curing Agent Component B and mixed for 5 minutes. The use of a paddle-head mixer on a slow speed drill is ideal.

For smaller areas the individual components can be carefully weighed into 1 Part resin A mixed with 8 Parts of curing agent B by weight. Follow all safety precautions as outlined in the SDS's when handling the components.

#### 5 Application and Usage

Squash Court Coating should be applied in 2 coats. The first coat may be thinned with 5% - 10% water to ensure maximum penetration into the substrate. Application on all surfaces is by brush or roller ensuring complete coverage of the substrate. The second coat should be applied within 24 hours and preferably as soon as the first coat is touch-dry.

#### 6 Cleaning

All tools and equipment can be cleaned with water or mineral spirits (Do not use solvents on hands).

#### 7 Health And Safety

It is recommended that barrier creams, gloves and protective clothing be used when working with RD36.

If eyes are affected wash with copious amounts of cold water and seek medical advice. For hands, wash with soap and warm water.

For full details see separate Safety Data Sheet.

#### 8 Coverage Rates

Coverage rate approximately 6-8m<sup>2</sup>/kg (2 coat application)

One 5.4kg unit will cover approximately 38m<sup>2</sup> (380 ft<sup>2</sup>) for a 2 coat application.

#### 9 Storage

Store in good dry conditions between 5 – 25°C. The shelf life of Armourcoat Squash Court Coatings (Parts A & B) in unopened original packaging, under correct storage conditions is 12 months from date of manufacture.

Whilst every attempt has been made to ensure the accuracy and reliability of the information contained in this document, the information should not be relied upon as a substitute for formal advice. Armourcoat Ltd, its employees and agents will not be liable for any loss or damage, of any kind, arising out of or in connection with the use of this document. Please refer to the company disclaimer for further details.

SAT PDS21 0408(1)©

#### Armourcoat Limited

Morewood Close London Road  
Sevenoaks Kent TN13 2HU United Kingdom  
Tel: +44 (0)1732 460 668 Fax +44 (0)1732 450 930  
Email: technical@armourcoat.co.uk  
web: www.armourcoat.com