

Product Data Sheet PDS9

For full application details please refer to 'Polished Plaster Application Manual'.

Aquawax

1 Product Description

Aquawax is an anionically stabilized, aqueous dispersion of various waxes and additives. This product is suitable for coating porous surfaces where it will impart water resistant and stain resistant properties.

2 Properties

- Enhances both the decorative and physical properties of porous products.
- Quick and easy to apply and economically priced.
- Water based product with low VOC emissions and low odour.
- Supplied ready for use on site.
- Imparts good water resistance.
- Imparts improved stain resistance.
- Easy to clean.

3 Health And Safety

Aquawax is water based, non-combustible and has low VOC emissions. It is non-hazardous; but in keeping with good working practices, avoid prolonged skin contact. For further details, refer to 'Aquawax Material Safety Data Sheet'.

4 Suitable Substrates

Can be applied over all polished plaster finishes where vapour permeability is not a requirement.

Abide by the substrate recommendations as set out in 'Polished Plaster Application Manual'.

For areas requiring a high gloss finish White Wax may be more suitable.

5 Applying Aquawax

Make sure that the polished plaster has been allowed to dry for 24 hours minimum.

Liberally apply a first coat of Aquawax using a cloth, sponge or roller. Wipe off any drips or runs as you go.

Within a few minutes, using a cloth moistened with a little wax in one hand and a dry cloth in the other, first wipe the damp cloth onto around ¼ m² at a time to remove the swirl marks, and then polish with the dry cloth. Dark patches will disappear as the wax dries.

Leave the Aquawax to dry for 1-2 hours and buff with a mechanical buffer to enhance the surface shine.

6 Coverage Rates

Smooth Finishes (Spatulata, Smooth, Cloudy, Armuralia etc.)
Coverage rate approximately 27 m²/lt

Textured Finishes (Pitted, Dragged)
Coverage rate approximately 12 m²/lt

Travertine
Coverage rate approximately 8 m²/lt

7 Storage

Aquawax must be protected from freezing and preferably stored at 5°C-25°C at all times.

Aquawax has a shelf life of 12 months under good storage conditions.

Whilst every attempt has been made to ensure the accuracy and reliability of the information contained in this document, the information should not be relied upon as a substitute for formal advice. Armourcoat Ltd, its employees and agents will not be liable for any loss or damage, of any kind, arising out of or in connection with the use of this document. Please refer to the company disclaimer for further details.

SAT PDS9 0504©

Armourcoat Limited

Morewood Close London Road
Sevenoaks Kent TN13 2HU United Kingdom
Tel: +44 (0)1732 460 668 Fax +44 (0)1732 450 930
Email: technical@armourcoat.co.uk

web: www.armourcoat.com